

Docket No. JM 7343-1
Application No. 10/736,117
Page 2

AMENDMENTS TO THE CLAIMS:

This listing of claims will replace all prior versions, and listings, of claims in the application:

LISTING OF CLAIMS:

Claim 1 (Currently Amended): A woven, patterned glass fiber textile fabric comprised of a glass fiber yarn with a titer of from ~~10 to 125~~ about 30 to 75 tex as the warp, and a glass fiber yarn having a titer ranging from ~~68 to 660~~ 190 to 350 tex as the weft, wherein the warp density of the fabric ranges from ~~2.5 to 20 thread/cm~~ 2.5 to 5 threads/cm and the weft density ranges from 2.0 to 12 threads/cm.

Claim 2 (Canceled).

Claim 3 (Original): The glass textile fabric of claim 1, wherein the titer of the warp yarn is about 34 tex.

Claim 4 (Original): The glass textile fabric of claim 1, wherein the titer of the warp yarn is about 70 tex.

Claim 5 (Canceled).

Claim 6 (Original): The glass textile fabric of claim 1, wherein the titer of the weft yarn is about 200 tex.

Docket No. JM 7343-1
Application No. 10/736,117
Page 3

Claim 7 (Original): The glass textile fabric of claim 1, wherein the titer of the weft yarn is about 330 tex.

Claims 8 - 10 (Canceled):

Claim 11 (Original): The glass textile fabric of claim 1, wherein the textile is impregnated with a chemical formulation comprised of a starch binder and a polymeric binder.

Claim 12 (Withdrawn-Currently Amended): A method of making ~~[[a]]~~ the woven, patterned glass fiber textile of claim 1, comprising the following steps: providing a patterned control Jacquard loom, and weaving a textile using ~~[[a]]~~ the glass fiber warp yarn ~~with a titer from 10 to 125 tex, and using a~~ the glass fiber weft yarn ~~with a titer ranging from 68 to 660 tex of claim 1.~~

Claim 13 (Withdrawn): The method of claim 12, wherein the titer of the glass fiber warp yarn ranges from 30 to 75 tex.

Claim 14 (Withdrawn): The method of claim 12, wherein the titer of the glass fiber warp yarn is about 34 tex.

Claim 15 (Withdrawn): The method of claim 12, wherein the titer of the glass fiber warp yarn is about 70 tex.

Docket No. JM 7343-1
Application No. 10/736.117
Page 4

Claim 16 (Withdrawn): The method according to claim 12, wherein the titer of the weft yarn ranges from about 190 to 350 tex.

Claim 17 (Withdrawn): The method of claim 12, wherein the warp density of the textile ranges from 2.5 to 5 threads/cm.

Claim 18 (Withdrawn): The method of claim 12, wherein the weft yarn density ranges from about 2.0 to 12 threads/cm.

Claim 19 (Withdrawn): The method of claim 12, wherein the textile is further impregnated with a chemical formulation comprised of a starch binder and a polymeric binder.